



DuraForm® ProX® AF+

DuraForm ProX AF+ is an aluminum filled nylon 12 plastic that produces parts with high stiffness and a metallic appearance

General Properties

MEASUREMENT	CONDITION	METRIC	U.S.
Sintered Part Density @ 23 °C	ASTM D792	1.31 g/cc	0.047 lbs/in ³
Moisture Absorption @ 23 °C	ASTM D570	0.25 %	0.25 %

Mechanical Properties

MEASUREMENT	CONDITION	METRIC	U.S.
Tensile Strength Yield, Ultimate (MPa psi)	ASTM D638	37.0	5350
Tensile Modulus (MPa ksi)	ASTM D638	4340	630
Elongation at Break (%)	ASTM D638	3	3
Flexural Strength, Ultimate (MPa psi)	ASTM D790	64	9260
Flexural Modulus (MPa ksi)	ASTM D790	3710	538
Hardness, Shore D	ASTM D2240	78	78
Impact Strength (J/m ft-lb/in) Notched Izod Unnotched Izod	ASTM D256	54 255	1.0 4.8

Features

- Excellent surface finish
- Easily machined and polished for the addition of press fits, tappings or other uses
- Repeatable mechanical properties for consistent prints time after time
- High stiffness for rigid functional assemblies
- Improved recyclability for an aluminum filled powder

Benefits

- Aesthetic metallic surface finish directly off the printer
- Complex designs can have a metallic look with functional strength at an affordable cost
- High rigidity ideal for jigs and fixtures
- Excellent stiffness to weight ratio
- Lower cost per part due to higher recyclability

Applications

- Housing and enclosures
- Plastic parts requiring a metallic finish and good appearance
- Automotive styling parts where a metallic look is needed (knobs, bezels etc.)
- High rigidity components
- Wind tunnel testing parts where stiffness and light weight are needed



DuraForm[®] ProX[®] AF+

DuraForm ProX AF+ is an aluminum filled nylon 12 plastic that produces parts with high stiffness and a metallic appearance

Thermal Properties

MEASUREMENT	CONDITION	METRIC	U.S.
Heat Deflection Temperature @ 0.45 MPa @ 1.82 MPa	D648	182 °C 174 °C	360 °F 345 °F
Coefficient of Thermal Expansion (0-145 °C) (µm/m-°C µin/in-°F)	E831	145	81
Specific Heat Capacity @ 23 °C (J/g-°C BTU/lb-°F)	E1269	1.44	0.34
Thermal Conductivity (W/m-K in/hr-ft ² -°F)	E1530	0.42	2.91
Flammability	UL 94	HB	HB

Electrical Properties

MEASUREMENT	CONDITION	METRIC	U.S.
Volume Resistivity (ohms-cm ohms-in)	ASTM D257	1.09 x 10 ¹⁴	4.29 x 10 ¹³
Surface Resistivity (ohm)	ASTM D257	1.33 x 10 ¹³	1.33 x 10 ¹³
Dissipation Factor, 1 KHz	ASTM D150	0.0121	0.0121
Dielectric Constant, 1 KHz	ASTM D150	2.6	2.6
Dielectric Strength (kV/mm kV/mil)	ASTM D149	3	77



3D SYSTEMS[®]

www.3dsystems.com

The parts used to generate the above data were generated by building parts using 70% virgin powder using default parameters on a ProX[®] SLS 500 printer.

Warranty/Disclaimer: The performance characteristics of these products may vary according to product application, operating conditions, or with end use. 3D Systems makes no warranties of any type, express or implied, including, but not limited to, the warranties of merchantability or fitness for a particular use.

© 2017 by 3D Systems, Inc. All rights reserved. Specifications subject to change without notice. 3D Systems, ProX and DuraForm are registered trademarks and the 3D Systems logo is a trademark of 3D Systems, Inc.